



# Den Braven

## Technical Data Sheet

### Zwaluw Repox®

2-component elastic and paintable wood repair compound based on epoxy resins



### Product Description

Zwaluw Repox® is a permanently elastic solvent free 2-component wood repair system. It is meant for small and large repairs based on epoxy resin. Zwaluw Repox® comes with a COT report LAB12-0117-RAP and complies with the regulation according the COT quality description 04.20 Wood Repair Compound.

### Benefits

- Apply directly from the cartridge using a professional caulking gun
- Non shrinking, high flow resistance, moisture resistant
- Almost odourless
- Ready to use
- For small and large repairs
- Primer not necessary
- For interior and exterior use

### Applications

Zwaluw Repox® was specifically developed for repairing defects or wood rot in construction of both new and existing wood. Suitable for all types of repairs from 10 mm up to 20 cm, and volumes up to approx. 1.5 liters. For use on doors, window frames, stairs and sheet material such as chipboard, blockboard and plywood. Also as a repair compound for furniture. Suitable for interior and exterior use.

### Directions Of Use

Suitable for repairs from 10 mm up to 20 cm, and a maximum of 1,5 liter.

### Additional information

|  |                |                |
|--|----------------|----------------|
| Application temperature                |                | +2°C to +30°C  |
| Density                                |                | 1,45 g/ml      |
| Frost resistance during transportation |                | Up to -15°C    |
| Paintable                              | @ +23°C/50% RH | > 6 hours      |
| Sandable                               | @ +23°C/50% RH | 4-6 hours      |
| Temperature resistance                 |                | -20°C to +80°C |

*These are typical values*

### Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Can not be applied with an air pressure gun

### Surface Preparations and Finishing

Zwaluw Repox® does not require primer. The treatment area must be dry, clean and free from oil. Remove loose parts and old peeling paint. Remove weathered, damaged and rotten parts of the wood with a chisel or router leaving the healthy wood exposed. The area of the repair should be sharp angled. Never let the wood taper off. Apply Zwaluw Repox® at ambient temperatures of +2°C. By keeping the cartridge at a temperature of +15°C the drying process will not be delayed.

### Paintability

Zwaluw Repox® can be sanded after 4-6 hours and is paintable after 6 hours with water based and synthetic based paints. If you a sanding time of 15 minutes and a paintability of 30 minutes is required, then apply the Zwaluw Repox. We recommend testing compatibility with paint prior to application.



Den Braven

Arkema Middle East DMCC  
Unit 1108 JBC 3 Tower, Cluster Y, Jumeirah Lakes Towers, P.O. Box 336393 Dubai  
T +971 48751704 | E bostik.mena-info@bostik.com

18-05-2024  
18:49:29  
CEST



# Den Braven

Better  
results  
through  
knowledge

## Technical Data Sheet

### Zwaluw Repox®

2-component elastic and paintable wood repair compound based on epoxy resins

#### Cleaning

Uncured material and tools can be cleaned by using Zwaluw Cleaner.

Cured material can only be mechanically removed. Hands can be cleaned with Zwaluw Wipes.

#### Colour(s)

- Beige

#### Packaging

- Cartridge

*For product specifications, please refer to the Product Detail Page*

#### Shelf Life

In unopened original packaging between +5°C and +25°C, shelf life till 12 months after production date, stored in a dry place.

#### Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

#### Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification

#### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.



Den Braven

Arkema Middle East DMCC  
Unit 1108 JBC 3 Tower, Cluster Y, Jumeirah Lakes Towers, P.O. Box 336393 Dubai  
T +971 48751704 | E [bostik.mena-info@bostik.com](mailto:bostik.mena-info@bostik.com)

18-05-2024  
18:49:29  
CEST