

# Technical Data Sheet

## Zwaluw Maxi PU foam B3

Professional polyurethane foam with high yield



## Product Description

Zwaluw Maxi PU foam B3 is a 1-component insulation and construction foam developed to create a seal between construction parts. Zwaluw Maxi PU foam B3 cures in response to moisture from the air and the building material.

### Benefits

- High quality professional PU Foam
- High yield

### Applications

Zwaluw Maxi PU foam B3 was developed to fill joints around window frames and in construction. Also for use in partition walls, ceiling and floor joints, surface penetration of pipes and tubes through walls and floors. Zwaluw Maxi-Gunfoam has excellent adhesion to concrete, brick, stone, plaster, wood, metal and many plastics like EPS and XPS, rigid PU foam and uPVC.

## **Directions Of Use**

Canister temperature: +5°C to +30°C (recommended +15°C to +25°C) Application temperature (applies to environment and substrates): +5°C to +35°C (recommended +15°C to +25°C) Remove cap and screw the straw firmly onto the valve. Shake the canister vigorously prior to use at least 20 times. To apply foam, turn the canister upside down and press the adaptor. Half fill the cavity and, in case of low humidity, lightly spray the foam with water. The foam will expand to fill the rest. When fixing window frames, use spacers and wedges to hold the frame in place for approximately 24 hours until the foam is fully cured. Protect eyes, wear gloves and protective gear. Floor-covering and furniture to be covered with paper or plastic foil. Joints wider and deeper than 4cm should be filled in multiple layers. Wait 15-30 minutes between applications. Before each application lightly spray with water. Only use in well ventilated areas. Store canister upright between +5°C and +25°C. Pressurized container! Protect from sunlight and do not expose to temperatures exceeding

+50°C. Do not pierce or burn, even after use. Contains flammable propellants. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition. No smoking. For more information see Technical Bulletins in the Knowledge Base on our website www.denbraven.com.

### Additional information

Application temperature		+5°C to +35°C
Base		Polyurethane
Closed cells		±70%
Curing time		100-120 minutes
Cutting time	EN 17333-3	60-80 minutes
Density		20-30 kg/m³
Fire behaviour		В3
Tack free time	EN 17333-3	10-15 minutes
Temperature resistance		-40°C to +90°C
Thermal conductivity		30-35 mW/m.K
Total foam yield	EN 17333-1	750 ml = 30-35 liter

These are typical values

### Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable for permanent water load. Not suitable for use (eg filling) in cavities with insufficient moisture

### Surface Preparations and Finishing

Substrates must be clean and free of dust, oil and grease. It is important to moisten substrates slightly before use as this improves adhesion and finished cell structure of the foam.

### Paintability

Can be painted or covered with sealant/plaster when fully cured.



#### Arkema Middle East DMCC



# **Technical Data Sheet**

## Zwaluw Maxi PU foam B3

Professional polyurethane foam with high yield

## Cleaning

Fresh foam can be removed immediately with Zwaluw Universal PU-Cleaner. After curing surplus foam can be removed with a knife or spatula and the foam surface can be finished.

## Colour(s)

Yellow

## Packaging


Aerosol

For product specifications, please refer to the Product Detail Page

### Shelf Life

If kept stored in a cool, dry place, in unopened orignal packaging, between +5°C and +25°C, shelf life is up to 18 months from production date. Store the canisters in an upright position.

## Certifications



## Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

### Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

#### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostk. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostk written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostk is not lable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document. Bostk is cannot be held liable for any damage, either directly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

